

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>6</sup> : B29D 67/20, C08J 9/06	A1	(11) International Publication Number: WO 99/51425	(43) International Publication Date: 14 October 1999 (14.10.99)
--	----	---	--

(21) International Application Number: PCT/US99/07312  
(22) International Filing Date: 1 April 1999 (01.04.99)  
(30) Priority Data:  
09/055,098 3 April 1998 (03.04.98) US  
(71) Applicant (for all designated States except US): CERTAIN-  
TEED CORPORATION [US/US]; 750 E. Swedesford Road,  
P.O. Box 860, Valley Forge, PA 19482-0101 (US).  
(72) Inventors; and  
(75) Inventors/Applicants (for US only): STUCKY, David, J.  
[US/US]; 108 East Princess Drive, Brooklyn, MI 49230  
(US). ELINSKI, Randall [US/US]; 5405 Squire Manor,  
Jackson, MI 49201 (US).  
(74) Agents: KOFFS, Steven, E. et al.; Duane, Morris & Heckscher  
LLP, One Liberty Place, Philadelphia, PA 19103-7396  
(US).


(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG,  
BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB,  
GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG,  
KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK,  
MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI,  
SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA,  
ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ,  
UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD,  
RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK,  
ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI  
patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR,  
NE, SN, TD, TG).

Published  
With international search report.

(54) Title: FOAMED POLYMER-FIBER COMPOSITE

(57) Abstract

Foamed polymer-fiber composites (100), building materials and methods of making such building materials are provided by this invention. The composites include about 35-75 wt.% of a polymeric resin, about 25-65 wt.% fiber and have a specific gravity of less than about 1.25 g/cc. The low density is provided by the introduction of a blowing agent or gas into a molten precursor of the composite during thermoforming, such as in an extrusion operation.



**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

## **FOAMED POLYMER-FIBER COMPOSITE**

### **Field of the Invention**

5        This invention relates to polymer-fiber composites used for the fabrication of decking, railing, siding and structural materials, and more particularly, to foamed composites which are lightweight and provide adequate strength and mechanical properties for building requirements.

### **Background of the Invention**

10

Synthetic lumber has been used as a substitute for wood in areas where wood can deteriorate quickly due to environmental conditions. Although in the past, its commercialization was limited by costs, modern recycling techniques and low cost extrusion manufacturing capability have permitted greater penetration by polymer-fiber composite materials into the commercial and residential markets. One such product manufactured under the trademark TREX, by Trex Company, LLC, Winchester, VA, consists of a polyethylene-wood fiber blend which is extruded into board dimensions for decking applications. Polyethylene-wood composite boards in 5/4 inch thicknesses have sufficient rigidity to be used as decking planks, but typically are not recommended for structural wood substitutes, such as the lattice structure often used as a support for decks.

15  
20

Polyethylene composites are attractive because they permit screw fasteners to "countersink", such that the heads of the screws bury or at least become flush with the board surface, without predrilling. These synthetic wood products are weather resistant and relatively maintenance free. Once installed, they resist splintering and warping normally associated with wood boards. They are also characterized by "color weatherability"; for

25

example, the TREX product initially is a light coffee brown color and converts to a weathered gray appearance when exposed to rain water and sunlight.

Polyethylene-wood composite boards do not require painting, and never include knots which often result in damage to the surface of ordinary wood lumber, and usually more difficult hammering or screwing of fasteners. These composite materials also do not shed sap, and have a smooth surface texture that is comfortable for even barefoot walking.

In addition to polyethylene, other plastics have been suggested for use in the manufacture of synthetic wood products. Polyvinyl-chloride ("PVC") thermoplastics have been used in combination with wood fibers to make extruded materials, for use in windows and doors, for example. See U.S. Patent No. 5,486,553 assigned to Andersen Corporation. Such components are designed to substitute for structural wooden members and typically have a tensile or Young's modulus of about 500,000 psi or greater. Because they are often load bearing, some of these wood fiber-PVC reinforced articles are dense, relatively heavy, and are believed to require predrilling in order to countersink a screw head.

Accordingly, there remains a need for a building material that is light weight, and can permit the countersinking of a screw head without predrilling. There also remains a need for an extrudable polymer-fiber composite that can be tinted in a variety of permanent or semi-permanent colors or to provide a weathered look.

### **SUMMARY OF THE INVENTION**

This invention provides foamed polymer-fiber composite building materials which may include about 35-75 wt. % of the polymeric resin, about 25-65 wt. % fiber, and a

specific gravity of less than about 1.25g/cc. The resulting composite includes a plurality of pores or cells therein resulting from the addition of a blowing agent or disbursed gas into a molten precursor of the composite.

The composites of this invention are nearly 10% lighter than non-foamed synthetic boards of similar composition. The preferred vinyl-resin boards are stiffer than polyethylene wood composites of similar thickness. PVC can be foamed through the addition of a blowing agent to a compounded mixture of resin and wood flour. This results in a preferred amount of porosity of at least about a 1% by volume of solids, concentrated primarily in a central region of the cross-section of extruded composite forms made from these mixtures. The tensile and flexural modulus of the preferred board-like members of this invention is less than about 500,000 psi, and generally about 100,000 to 450,000 psi. The resulting board-like surfaces permit the countersinking of screw heads without predrilling.

The polymer-fiber composites of this invention can also include additives for improving the melt strength of a molten precursor of the composite during extrusion operations. The preferred additives for this purpose include acrylic modifiers in amounts ranging from .1 to about 15 weight percent. Building materials made from such composites can be tinted to provide a weathered look through the addition of dyes, such as mixed metal oxides and titanium dioxide, pigments, or flyash, for example. In order to reduce costs, larger wood flour particles greater than 30 mesh size can be used.

#### **Brief Description of the Drawings**

FIG. 1: is a partial, cross-sectional, front perspective view of a preferred foamed polymer-fiber composite building material of this invention;

FIG. 2: is a front perspective, partial view, of a deck construction and home using the preferred composite building materials of this invention;

FIG. 3: is a side, cross-sectional view of the composite building material of FIG. 1 illustrating a screw which has been inserted in a counter-sink relationship with a top surface  
5 of the building material;

FIG. 4: is a partial, cross-sectional, front perspective view of a preferred railing of this invention;

FIG. 5: is a graph depicting specific gravity versus wood flour concentration for the composites of this invention;

10 FIG. 6: is a graph depicting specific gravity versus acrylic modifier concentration for the composites of this invention;

FIG. 7: is a graph depicting specific gravity versus chemical blowing agent concentration for the composites of this invention;

15 FIG. 8: is a graph depicting flexural modulus versus wood flour concentration for the composites of this invention;

FIG. 9: is a graph depicting flexural modulus versus acrylic modifier concentration for the composites of this invention;

FIG. 10: is a graph depicting flexural modulus versus chemical blowing agent concentration for the composites of this invention;

20 FIG. 11: is a graph depicting flexural strength versus wood flour concentration for the composites of this invention;

FIG. 12: is a graph depicting flexural strength versus acrylic modifier concentration for the composites of this invention; and

FIG. 13: is a graph depicting flexural strength versus chemical blowing agent concentration for the composites of this invention.

### Detailed Description of the Invention

5

The foamed polymer-fiber composites of this invention can be used by themselves, or in conjunction with "capstock" or coextrusions of other materials, such as, for example, pure or copolymer resins, resins filled with wood or glass fiber, or additives, such as sand, to provide better traction, strength, ultraviolet protection or textures to provide a more wood-like appearance. This invention also pertains to a process for making foamed polymer-fiber composites, such as building materials, including roof shingles, siding, floor tiles, paneling, moldings, structural components, steps, door and window sills and sashes; house and garden items, such as planters, flower pots, landscape tiles, decking, outdoor furniture, fencing, and playground equipment; farm and ranch items, including pasture fencing, posts and barn components; and marine items, for example, decking, bulkheads and pilings.

un-foamed  
layer

As shown in the figures, and in particular, FIG. 1, there is shown a preferred foamed polymer-fiber composite 100 which includes about 35-75% of a polymeric resin, about 25-65% fiber with a specific gravity of less than about 1.25 g/cc, and preferably about .5-1.2 g/cc. This composite 100 includes a plurality of pores or cells defining porosity 20 therein resulting from the addition of a blowing agent or gas to a molten precursor of said composite 100. The porosity desirably measures at least about 1%, and preferably about 5-40% by volume of solids in the composite 100. The composites of this invention also may include one or more additives, such as a process aid, pigment, or plasticizer.

foam  
layer

As shown in FIGS. 2-4, the foamed polymer-fiber composite 100 of this invention is ideally suited for decking, siding, railings, window frames, including styles and rails, and balusters. Even though the composite 100 is light-weight, it generally has a flexural modulus, tensile modulus, and/or Young's modulus of about 100,000 to 450,000 psi. As shown in FIG. 3, the composite 100 preferably allows screw and nail fasteners, such as screw 35, to be secured in a countersink relationship with the surface of the composite 100 or below the surface, without predrilling. This is generally accomplished by the use of plasticizing agents to lower the compression strength of the composite 100, and/or by the careful use of blowing agents or gas in the molten precursor of the composite 100, so as to provide a cellular internal structure containing porosity 20 surrounded by a polymeric skin 10. This porosity, even without plasticizing agents, provides enough compressive strength relief to permit screw fasteners to countersink without predrilling. This permits a very attractive deck 40 of side-by-side composite boards as shown in FIG. 2. Ideally, for strength and cost considerations, the support structure and columns of the deck are made from wood.

Also as shown in FIG. 2, the preferred composite 100 can be fashioned, for example, by extrusion, in the shape of siding 55 or window frame components 58, such as styles or rails, for a house 50. As shown in FIG. 4, the composite 100 can also be shaped into a railing 45 or baluster 60.

The preferred materials of this invention will now be described in more detail. The composites generally contain about 35-75 wt.% resinous materials, such as thermoplastic and thermosetting resins, for example, PVC, polyethylene, polypropylene, nylon, polyesters, polysulfones, polyphenylene oxide and sulphide, epoxies, cellulose, etc. A preferred thermoplastic material for the panels of this invention is PVC. PVC thermoplastics comprise



the largest volume of thermoplastic polymers in commercial use. Vinyl chloride monomer is made from a variety of different processes involving the reaction of acetylene and hydrogen chloride and the direct chlorination of ethylene. Polyvinyl chloride is typically manufactured by the free radical polymerization of vinyl chloride. After polymerization, polyvinyl chloride is commonly combined with impact modifiers, thermal stabilizers, lubricants, plasticizers, organic and inorganic pigments, fillers, biocides, processing aids, flame retardants or other commonly available additive materials, when needed. Polyvinyl chloride can also be combined with other vinyl monomers in the manufacture of polyvinyl chloride copolymers. Such copolymers can be linear copolymers, graft copolymers, random copolymers, regular repeating copolymers, block copolymers, etc. Monomers that can be combined with vinyl chloride to form vinyl chloride copolymers include acrylonitrile; alpha-olefins such as ethylene, propylene, etc.; chlorinated monomers such as vinylidene, dichloride; acrylate monomers such as acrylic acid, methylacrylate, methyl-methacrylate, acrylamide, hydroxethyl acrylate, and others; styrenic monomers such as styrene, alpha methyl styrene, vinyl toluene, etc.; vinyl acetate; or other commonly available ethylenically unsaturated monomer compositions. Such monomers can be used in an amount of up to about 50 mol-%, the balance being vinyl chloride. PVCs can be compounded to be flexible or rigid, tough or strong, to have high or low density, or to have any of a wide spectrum of physical properties or processing characteristics. PVC resins can also be alloyed with other polymers, such as ABS, acrylic, polyurethane, and nitrile rubber to improve impact resistance, tear strength, resilience, or processability. They can be produced water-white in either rigid or flexible compositions, or they can be pigmented to almost any color.

In the preferred embodiments of this invention, rigid PVC, optionally containing a small amount of plasticizer, is employed. This material is a hard and tough and can be compounded to have a wide range of properties, including impact resistance and weatherability, e.g., fading color to a wood grey appearance. It also has a tensile strength of about 6,000-7,500 psi, a percent elongation of about 40-80%, and a tensile modulus of about 3.5-6.0X10<sup>6</sup> psi. It can be acceptably used without chlorination, to about 140° F., and with chlorination to about 220° F. It also has a coefficient of thermal expansion of about 3-6X10<sup>-5</sup> inch/inch-°F.

The composite building materials of this invention can be injection or vacuum molded, extruded and drawn, using customary manufacturing techniques for thermoplastic and thermosetting materials. In the preferred embodiment, a mixture of PVC regrind or virgin compound is compounded and then heated and extruded through a die to produce boards and other shapes having a length of about 4-20 feet and thicknesses ranging from .05 - 6.0 inches. The extruded thermoplastic boards can be subject to further molding, calendaring, and finishing to provide a wood grain or fanciful texture.

The building material 100 of this invention also can contain about 25-60 wt.% fiber, such as glass, wood, cotton, boron, carbon, or graphite fibers. Additionally, inorganic fillers, such as calcium carbonate, talc, silica, etc. can be used. Preferrably, the fibers are "cellulosic" in nature. Cellulosic fibers can be derived from recycled paper products, such as agrifibers, pulp, newsprint, soft woods, such as pine, or hard woods from deciduous trees. Hard woods are generally preferred for fiber manufacture because they absorb less moisture. While hard wood is the primary source of fiber for the invention, additional fiber make-up can be derived from a number of secondary sources including soft wood fibers, natural fibers

including bamboo, rice, sugar cane, and recycled or reclaimed fiber from newspapers, cardboard boxes, computer printouts, etc. This invention can utilize wood flour of about 10-100 mesh, preferably 20-30 mesh.

Preferably, this invention combines the resin and wood flour components with a  
5 chemical blowing agent, or introduces a gaseous medium into a molten mixture of the resin and wood fiber to produce a series of trapped bubbles prior to thermo-forming the mixture, for example, by molding, extrusion or co-extrusion. Such processes for making rigid foam articles are generally well known.

In the preferred processes of this invention, a quantity of PVC regrind in small chunks  
10 is mixed with 20-30 mesh wood flour of about grass-seed size which has been pre-dried to release any trapped moisture as steam. The mixture also includes a melt enhancer, such a high molecular weight acrylic modifier, which improves melt elasticity and strength and enhances cellular structure, cell growth and distribution.

A chemical blowing agent or gas can also be added to the mixture to reduce the  
15 density and weight of the composite 100 by foaming. If a chemical blowing agent is used, it is mixed into the compound during blending or at the feed throat of the extruder. In the extruder, the blowing agent is decomposed, discharging gas, such as nitrogen or CO<sub>2</sub>, into the melt. As the melt exits the extrusion die, the gas sites experience a pressure drop expanding into small cells or bubbles trapped by the surrounding polymer.

20 Chemical blowing agents can be any of a variety of chemicals which release a gas upon thermal decomposition. Chemical blowing agents may also be referred to as foaming agents. The blowing agent, or agents, if more than one is used, can be selected from chemicals containing decomposable groups such as azo, N-nitroso, carboxylate, carbonate,

hetero-cyclic nitrogen-containing and sulfonyl hydrazide groups. Generally, they are solid materials that liberate gas when heated by means of a chemical reaction or upon decomposition. Representative compounds include azodicarbonamide, bicarbonates, dinitrosopentamethylene tetramethylene tetramine, p,p'-oxy-bis (ben-zenesulfonyl)-  
5 hydrazide, benzene-1,3-disulfonyl hydrazide, aso-bis-(isobutyronitrile), biuret and urea.

The blowing agent may be added to the polymer in several different ways which are known to those skilled in the art, for example, by adding the solid power, liquid or gaseous agents directly to the resin in the extruder while the resin is in the molten state to obtain uniform dispersion of the agent in the molten plastic. Preferably the blowing agent is added  
10 before the extrusion process and is in the form of a solid. The temperature and pressure to which the foamable composition of the invention are subjected to provide a foamed composition will vary within a wide range, depending upon the amount and type of the foaming agent, resin, and cellulosic fiber that is used. Preferred foaming agents are selected from endothermic and exothermic varieties, such as dinitrosopentamethylene tetramine, p-  
15 toluene sulfonyl semicarbazide, 5-phenyltetrazole, calcium oxalate, trihydrazino-s-triazine, 5-phenyl-3, 6-dihydro-1,3,4-oxadiazin-2-one, 3,6-dihydro 5,6-diphenyl-1,3,4 oxadiazin-2-one, azodicarboamide, sodium bicarbonate, and mixtures thereof.

In addition to the above, a coloring agent can be added to the compounded mixture, such as dyes, colored pigments, or flyash, or a mixture of these ingredients depending on the  
20 resulting color, and cost considerations. Such additives can provide "weatherability" or a faded greyish coloring or a permanent tint, such as blue, green or brown. This invention can be further understood by reference to the following examples.

### **EXAMPLES**

Examples 1-16 were formulated and extruded into test boards. Mechanical properties of each formulation were measured and compared.

**Table I - Parts per hundred parts resin (PHR), and  
Weight per cent (WT%) vs.  
Property of Selected Formulations**

FORMULATION	PHR			WT%					PROPERTY		
	RIGID PVC COMPD	WOOD FLOUR	ACRYLIC MODIFIER	BLOWING AGENT					SPECIFIC GRAVITY (g/cc)	FLEX MODULUS (psi)	FLEX STRENGTH (psi)
1	100	68	4	0.5	57.97	39.42	2.32	0.29	1.16	421037	4823
2	100	100	10	0.5	47.51	47.51	4.75	0.24	1.07	398042	4286
3	100	100	4	1.5	48.66	48.66	1.95	0.73	1.09	297233	3397
4	100	68	10	1.5	55.71	37.88	5.57	0.84	0.83	205162	3158
5	100	100	4	0.5	48.90	48.90	1.96	0.24	1.17	357212	3790
6	100	68	10	0.5	56.02	38.10	5.60	0.28	1.09	457829	5353
7	100	68	4	1.5	57.64	39.19	2.31	0.86	1.06	287530	3964
8	100	84	7	0.5	52.22	43.86	3.66	0.26	1.11	431283	4769
9	100	84	4	1	52.91	44.44	2.12	0.53	1.02	260310	3386
10	100	68	7	1	52.08	43.75	3.65	0.52	0.98	270421	3597
11	100	100	10	1.5	47.28	47.28	4.73	0.71	0.94	224739	3058
12	100	100	10	1	47.39	47.39	4.74	0.47	0.99	256923	3207
13	100	84	10	1.5	51.15	42.97	5.12	0.77	0.89	227991	3124
14	100	100	7	1.5	47.96	47.96	3.36	0.72	0.97	271955	2996
15	100	68	10	1	55.87	37.99	5.59	0.56	0.93	305704	4014
16	100	84	10	0.5	51.41	43.19	5.14	0.26	1.08	430736	4747

In comparing the properties, it was noted that to obtain a target flexural modulus of about 200,000 psi, the following preferred formula was used.

**TABLE II: PREFERRED FORMULA**

5		<b>PPH PVC COMPOUND</b>
	Rigid PVC Compound	100
	20-30 Mesh Hardwood Flour	68
	Acrylic Modifier	10.0
	Chemical Blowing Agent	1.5
10	Carbon Black	.18

This formulation provided the most optimum combination of cost efficiency and mechanical properties.

From the foregoing, it can be realized that this invention provides improved foamed polymer wood composite materials which provide lower specific gravity and high flexural modulus while permitting countersinking of screw fasteners. They also have great durability and strength. Although various embodiments have been illustrated, this is for the purpose of describing, but not limiting the invention. Various modifications will become apparent to one skilled in the art, and are within the scope of this invention described in the attached claims.

**We Claim:**

1. A foamed polymer fiber composite building material, comprising: about 35-75 wt.% polymeric resin; about 25-65 wt.% fiber, and a specific gravity of less than about 1.25 g/cc, said composite building material including at least 1% porosity by volume of solids resulting from the addition of a gaseous medium or blowing agent to a molten precursor of said composite building material.
2. The wood composite building material of claim 1 further comprising an additive for improving the melt strength of said molten precursor.
3. The composite building material of claim 2 wherein said additive comprises an acrylic modifier.
4. The composite building material of claim 1 wherein said fiber comprises cellulosic fiber.
5. The composite building material of claim 1 wherein said molten precursor comprises about 0.1 to 2 wt.% of a chemical blowing agent and about .1 - 15 wt.% of an acrylic modifier.
6. The composite building material of claim 1 further comprising about 5-40% porosity by volume of solids.



7. The composite building material of claim 6 wherein said building material has a specific gravity of about .5-1.2 g/cc.

8. The composite building material of claim 1 further comprising an additive for producing a weathered appearance to said building material, said additive selected from the group comprising: a dye, pigment, flyash or a mixture thereof.

9. The composite building material of claim 1 including a flexural modulus of about 100,000 to 450,000 psi

10. A foamed polymer - wood composite, formed from a molten mixture comprising: about 35 - 75 wt.% polymeric PVC resin, about 25 - 65 wt.% wood fiber, and a blowing agent or gaseous medium, said molten mixture forming a polymer - wood composite having a specific gravity of less than about 1.25 g/cc, and a flexural modulus of about 100,000 - 450,000 psi.

15

11. The composite of claim 10 further comprising an additive for improving the melt strength of said molten mixture during extrusion.

12. The composite of claim 10 wherein said blowing agent comprises about 0.1 - 2.0 wt.% of a chemical blowing agent.

20

13. The composite of claim 12 wherein said chemical blowing agent is mixed into said polymeric resin and wood fiber during compounding, or at about the feet throat of an extruder.

14. The composite of claim 10 whereby said blowing agent produces a plurality of pores or cells within said composite for permitting a screw to be fastened flush to a surface of said composite without predrilling.

5 15. A method of forming a foamed polymer-cellulosic composite building material, comprising:

(a) compounding about 35 - 75 wt.% polymeric resin, about 25 - 65 wt.%  
cellulosic fiber, and about 0.1 to 2 wt.% of a blowing agent to form a compounded mixture;

10

(b) feeding said compounded mixture into an extruder, whereby said blowing agent becomes decomposed, disbursing a gas into said compounded mixture as it melts; and

(c) extruding said molten mixture containing said gas through a die whereby said  
15 gas forms tiny bubbles which are trapped within said polymer-cellulosic fiber composite.

16. The method of claim 15 wherein said compounded mixture further comprises a high molecular weight acrylic modifier for increasing melt elasticity and strength.



20 17. The method of claim 15 wherein said die comprises a generally board-shaped cross section.

18. A foamed polymer wood composite building material having a generally board-shaped cross-section, formed from a molten precursor comprising: about 45-60 wt.%

of a polyvinyl-chloride resin, about 35-55 wt.% wood flour, about .1-15 wt.% acrylic modifier; and about .1-2.0 wt.% of a chemical blowing agent; said building material having a specific gravity of less than about 1.25 g/cc and permitting a screw to be fastened flush to a surface of said building material without predrilling; said building material also comprising a  
5 flexural modulus of about 100,000-450,000 psi.

19. The composite building material of claim 18 wherein said polyvinyl-chloride resin comprises a compounded resinous mixture.

20. The composite building material of claim 18 wherein said building material  
10 comprises a pigment for producing a weathered wood-gray appearance.






FIG. 3







FIG. 4



## INTERNATIONAL SEARCH REPORT

International application No.

PCT/US99/07312

## A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) :B29D 67/20; C08J 9/06

US CL :264/45.8, 51, 54; 428/317.9; 521/79, 81

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 264/45.8, 51, 54; 428/317.9; 521/79, 81

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

NONE

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

NONE

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	POLYMER ENGINEERING AND SCIENCE, Volume 37, Number 7, issued July 1997, Matuana et al, "Processing and Cell Morphology Relationships for Microcellular Foamed PVC/Wood Fiber Composites", pages 1137-1147.	1, 2, 4, 6, 7, 9-15, 17
—		—
Y		3, 5, 8, 16, 18-20
Y	US 3,983,295 A (MURER et al) 28 September 1976, column 5, lines 10-27.	3, 5, 8, 16, 18-20

☐ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* Special categories of cited documents:	*T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
*A* document defining the general state of the art which is not considered to be of particular relevance	*X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
*B* earlier document published on or after the international filing date	*Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
*L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*g* document member of the same patent family
*O* document referring to an oral disclosure, use, exhibition or other means	
*P* document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

21 JUNE 1999

Date of mailing of the international search report

08 JUL 1999

Name and mailing address of the ISA/US  
Commissioner of Patents and Trademarks  
Box PCT  
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

BLAINE R. COPENHEAVER

Telephone No. (703) 308-0661